

POLYOLEFIN RESIN COMPOSITION FOR WHEEL COVER OF AN AUTOMOBILE

FIELD OF THE INVENTION

5 The present invention relates to a polyolefin resin composition for a wheel cover of an automobile. More particularly, it relates to a polyolefin resin composition comprising a high-crystalline olefin resin, a polyolefin based elastomer, and an inorganic filler chosen from glass beads coated with a polypropylene grafted with unsaturated carbonic acid or its anhydride and
10 barium sulfate, which is excellent in rigidity, impact strength, heat resistance, mechanical strength, moldability during injection molding, coatability, and appearance without protuberance on the welds and thus suitable for a wheel cover of an automobile. The invention also relates to the wheel cover.

BACKGROUND OF THE INVENTION

15 Polypropylene resins have been widely used in various fields due to relatively desirable price, lightweight and excellent mechanical strength. However, polypropylene resins exhibit unsatisfactory impact strength and rigidity. To overcome this deficiency, a polypropylene resin composition
20 containing ethylene-propylene copolymer rubber (EPM) and talc as an inorganic filler has been proposed.

 Conventional wheel covers of automobiles have been produced by press molding with steel. Recently, nylons and polyvinylphenylene oxides having excellent heat resistance have been used for lightening the weight of automotive
25 materials. However, use of these polymers has been a burden due to high cost to use such materials.

 Therefore, it has been proposed to use reinforced polyolefin resin compositions such as polypropylene for a low cost. For example, Japanese Laid-open publication no. 6-80839 discloses a wheel cover produced by

injection molding of a fiber-reinforced polypropylene resin composition comprising polypropylene, polypropylene having carboxylic acids, silan-treated glass fiber and polyethylene wax. Further, Japanese Laid-open publication no. 10-44701 discloses a wheel cover comprising polyolefin composition made of a crystalline propylene-ethylene block copolymer, an ethylene-propylene copolymer rubber, a polypropylene resin modified with unsaturated carbonic acid or its derivative, talc having less than 10 μm of an average particle diameter, and glass fiber.

Said polypropylene resin compositions for wheel covers use glass fiber to reinforce rigidity and inorganic talc to improve rigidity, impact resistance, and heat resistance. However, the most serious problem in the employment of them with respect to wheel covers is that they have a poor surface appearance quality due to protuberance on the welds.

SUMMARY OF THE INVENTION

Accordingly, an object of the present invention is to provide a polyolefin resin composition comprising a high crystalline olefin resin, a polyolefin based elastomer, and an inorganic filler chosen from glass beads coated with a polypropylene grafted with unsaturated carbonic acid or its anhydride and barium sulfate, so that the result is suitable for wheel covers due to excellent rigidity, impact resistance, heat resistance, and mechanical strength, moldability, coatability, and appearance without protuberance on the welds.

DETAILED DESCRIPTION OF THE INVENTION

The present invention is described in more detail set forth hereunder. The present invention provides a polyolefin resin composition for the automotive wheel cover comprising 40-75 wt.% of a high crystalline olefin resin, 3-25 wt.% of a polyolefin based elastomer and 5-30 wt.% of an inorganic filler.

High crystalline olefin resin used in the resin composition of the present

invention has a melt index of 10-80 g/10min (ASTM D 1238, 230 °C), preferably 20-60 g/10min. The propylene component has an isotactic pentad fraction of not less than 96%, for example between 97% and 100%, such as 99%. The high crystalline olefin resin improves flowability of olefin based elastomer and further improves the heat resistance, mechanical strength and thermal distortion. When the high crystalline olefin resin is used less than 40 wt.%, there is limitation to enhance heat resistance, mechanical strength and thermal distortion. On the other hand, when an isotactic pentad fraction of the polypropylene component is less than 96%, the properties of the high crystalline olefin resin such as rigidity, impact resistance, heat resistance and mechanical strength are deteriorated and the wheel cover obtained therefrom also has inferior heat resistance and mechanical strength.

Examples of the high crystalline olefin resin include a copolymer, random copolymer and a mixture thereof between propylene and a small amount of another α -olefin selected from isotactic polypropylene, propylene-ethylene copolymer, propylene-1-butane copolymer, propylene-1-hexene copolymer, and propylene-4-methyl-1-pentene copolymer. By small amount it is meant less than about 30%, typically less than about 20%, for example less than about 10% by weight.

The amount of high crystalline olefin resin is between 40% to 75 wt.%, for example between 50% and 65 wt.% by weight.

The polyolefin-based elastomer used in the resin composition of the present invention has a the Mooney viscosity ML_{1+4} (100 °C) of 10-100, preferably 20-70; a melt index of 0.5-10 g/10min (230 °C, 2.16 Kg), for example from about 3 to about 8 g/10min (230 °C, 2.16 Kg); and a co-monomer content of 10-40 wt.%, preferably 20-30 wt.%. The polyolefin based elastomer is used to provide an elasticity and flexibility and improve impact resistance, dispersion, and coatability. If a rubber having a Mooney viscosity of less than 10 is used, although the flowability is improved, the mechanical properties are inferior.

On the other hand, if a rubber having a Mooney viscosity of higher than 100 is used, although the mechanical properties are improved, the flowability is inferior.

5 The polyolefin based elastomer is chosen in one or more from ethylene-propylene copolymer rubber, ethylene-propylene-dicyclopentadiene rubber, ethylene-propylene-1,4-hexadiene rubber, ethylene-propylene cyclopentadiene rubber, ethylene-propylene-methylene-norbornane rubber, and ethylene-propylene-ethylidene-norbornane rubber. Also, the polyolefin based elastomer is chosen from hydrogenated styrene-butylene block copolymer (SEBS),
10 hydrogenated styrene-butadiene rubber (HSBR), styrene-ethylene-butylene block copolymer (SEBC) and crystalline ethylene-butylene block copolymer (CEBC).

The polyolefin based elastomer is used in the range of 3 to 25 wt.%, for example between 8 and 19 wt. %. When it is used less than 3wt. %, the impact resistance at a low temperature may be decreased. When it is used more than
15 25 wt.%, although the impact resistance is improved, the heat resistance and mechanical strength are decreased.

Inorganic filled used in the resin composition of the present invention is chosen from spherical glass beads, barium sulfate, and a mixture thereof and
20 used in the range of 5-30 wt.%, preferably 10-25 wt.%. When it is used less than 5 wt.%, the heat resistance and mechanical strength may be decreased during the molding process for the automotive wheel cover and the appearance quality is inferior due to protuberance on the welds. When it is used more than 30 wt.%, although the heat resistance and mechanical strength are good, the
25 impact resistance is decreased and the molecular weight of the molded wheel cover is increased.

The glass beads preferably have an average particle diameter of 15-45 μm , more preferably 20-40 μm , to improve the protuberance on the weld lines. When the average particle diameter is less than 15 μm , the appearance quality is

inferior due to protuberance on the welds. When the average particle diameter is more than 45 μm , although the mechanical strength and heat resistance are improved, the impact resistance is decreased.

Furthermore, the glass beads may be treated to improve the coatability and adhesion of the surface of the inorganic filler to the resin composition. It is preferred to use surface coated-glass beads, wherein the surface treatment increases compatability or adhesion to the resin composition. A preferred treatment of glass beads is coating them with a polypropylene grafted with unsaturated carbonic acid or its anhydride. The modified polypropylene for coating the surface of glass beads is prepared by melt-kneading a crystalline polypropylene, unsaturated carbonic acid or its anhydride and a catalyst with a twin-screw extruder at 180-220 $^{\circ}\text{C}$. The coating to glass beads can be in a weight ratio range of from about 1:1 to about 1:25, but is preferably 1:6 to 1:12, for example 1:9. In one embodiment, the modified polypropylene and glass beads having an average particle diameter of 15-45 μm were mixed in a ratio of 1 to 9 and melt-kneaded for coating the surface of the glass beads.

Barium sulfate used in the resin composition of the present invention has an average particle diameter of 0.1 to 5 μm , preferably 0.5-1 μm . When the average particle diameter is less than 0.5 μm , the composition does not mix well. When the average particle diameter is more than 1 μm , the appearance quality of the weld is inferior.

When the barium sulfate is used with the surface-modified glass beads, i.e., coated with the modified polypropylene, it exhibits a superior effect of improving the protuberance on the welds of automotive wheel covers.

Other additives, used by one having ordinary skill in the art, such as a reinforcing agent, a heat stabilizer, a weather stabilizer, an anti-static agent, a lubricant, a neutralizer, a flame retardant, wollastonite, calcium carbonate, mica, kaolin, clay, and calcium sulfate may be arbitrarily incorporated in an appropriate content not to obstruct the above-mentioned object of the present

invention.

In a less preferred embodiment, glass beads may be used with other inorganic fillers, for example wollastonite, calcium carbonate, mica, kaolin, clay, and calcium sulfate.

5 The following examples are intended to further illustrate the present invention without limiting its scope.

Symbols used in Examples and Comparative Examples are as follows:

1) Polypropylene

10 PPI-1 : a melt index of 30 g/10min(230 °C), a content of ethylene of 10.5 mol%, and an isotactic pentad fraction of not higher than 96% measured by NMR.

 PPI-2 : a melt index of 30 g/10min(230 °C), a content of ethylene of 10.5 mol%, and an isotactic pentad fraction of not less than 96% measured by NMR.

15 PPI-3 : a melt index of 30 g/10min(230 °C), a content of ethylene of 5.6 mol%, and an isotactic pentad fraction of not less than 96% measured by NMR.

2) Polyolefin based elastomer (EPM)

 EB-1 : Ethylene-propylene copolymer rubber, a Mooney viscosity ML_{1+4} (100 °C) of 70, and a propylene content of 27 wt.%.

 EB-2 : Hydrogenated styrene-butadiene block copolymer, a flow rate of 1.5 (230 °C, 2.16 Kg), and a styrene content of 20 wt.%.

 EB-3 : Ethylene-butene copolymer rubber, a Mooney viscosity ML_{1+4} (100 °C) of 44, and a butene content of 20 wt.%.

25

3) Surface-coated glass beads with a modified polypropylene resin

 GB-1 : Surface-coated glass beads with a weight ratio of modified polypropylene resin : glass beads of 1 : 9.

4) Barium sulfate (BaSO_4)

BaSO_4 : Barium sulfate having an average particle diameter of 0.5-1 μm .

5) Glass fiber

5 GF : Glass fiber having a length of 9 μm .

6) Inorganic filler : Talc

Talc : Talc having an average particle diameter of 4 μm .

10 7) Modified polypropylene resin

CP : Modified polypropylene resin grafted with maleic anhydride (modified rate = 0.4)

Examples 1-4 and Comparative Examples 1-4

15 The components and contents as in the Table 1 were mixed (glass fiber and glass beads were added from the side of the extruder). The composition was dried at 80 °C for 2 hours to remove moisture therein. The molded articles for testing were obtained by injection molding under an injection temperature of 200 °C, a molding temperature of 60 °C and an injection pressure of 60-100
20 bar.

Physical properties of the polyolefin resin composition prepared from Examples 1-4 and Comparative Examples 1-4 were tested by the following methods. The result is shown in Table 2.

Test Method

- 25
- A. Flexural modulus (MPa): Tested with ASTM D790A.
 - B. Izod impact resistance ($\text{kg}\cdot\text{cm}/\text{cm}^2$): Tested with ASTM D256 at 23°C.
 - C. Thermal distortion temperature (°C): Tested with ASTM D656.
 - D. Attachment-detachment repetition test : Attachment of each wheel

cover to a wheel disc and detachment were repeated for 30 times and the occurrence of a trouble such as cracking was investigated.

E. Falling ball test : A steel ball was gravity-dropped on the decorative surface of each wheel cover at -30 °C.

5 F. Protuberance on the weld : Measured for the thickness of the weld (when the thickness was higher than 10 μm, it was failed).

Table 1

Category (wt.%)	Example				Comparative Example			
	1	2	3	4	C-5	C-6	C-7	C-8
PPI-1	-	-	-	-	-	57	63	-
PPI-2	65	-	65	63	60	-	-	60
PPI-3	-	63	-	-	-	-	-	-
EB-1	-	-	15	-	-	15	-	-
EB-2	15	-	-	-	15	-	-	-
EB-3	-	12	-	-	-	-	12	-
EB-4	-	-	-	17	-	-	-	15
GB-1	10	5	15	5	-	-	-	-
BaSO ₄	10	20	5	15	-	-	25	-
Talc	-	-	-	-	20	20	-	10
GF	-	-	-	-	-	5	-	15
CP	-	-	-	-	5	3	-	-

Table 2

Category		Example				Comparative Example			
		1	2	3	4	C-5	C-6	C-7	C-8
Flexural modulus (MPa)		3000	2400	3200	2100	2100	2050	1780	2500
Izod impact resistance (kg·cm/cm ²)		22	20	20	20	28	19	15	21
Thermal distortion temperature (□)		155	135	155	145	130	135	115	155
Attachment-detachment repetition test		O	O	O	O	O	O	X	O
Falling ball test for cracking		O	O	O	O	O	O	X	O
Appearance of the wheel cover		O	O	O	O	O	O	O	O
Welds	Appearance	O	O	O	O	X	X	O	X
	Protuberance height (μm)	5.8	1.2	6.2	2.3	62	43	7.2	34
O : Good, X : Poor									

As shown in Table 2, the polyolefin resin compositions of Examples 1-4 have excellent rigidity, impact resistance, heat resistance, attachment-detachment strength, and falling impact resistance and especially. Further, the weld appearances are superior and the protuberance height is not greater than 10 μm, preferably not greater than about 6 μm.

Although the polyolefin resin compositions of Comparative Examples 5, 6, and 8 show excellent rigidity and impact resistance, the appearance on the welds are poor and the protuberance heights are higher than 20 μm. Although the polyolefin resin compositions of Comparative Example 3 provides good

weld appearance with not higher than 10 μm of protuberance height, this composition shows poor rigidity, heat resistance, attachment-detachment strength, and falling impact resistance.

5 In some embodiments, the weight ratio of glass beads, especially surface-treated glass beads, to the inorganic filler with an average particle diameter of less than 1 micron, preferably particulate BaSO_4 , is between about 6:1 to about 1:10, preferably between about 2:1 to about 4:1.

10 As described above, the polyolefin resin composition of the present invention provides excellent rigidity, impact strength, heat resistance, mechanical strength, moldability, coatability, and appearance without protuberance on the welds and thus suitable for a wheel cover of an automobile.

15

20

25